

Article Collection SILKASH **AUTUMN/WINTER 25-26** Count Yarn Custom Code NM. 2/26 51062099 Washing Symbols Composition 15% WS 30% SE 55% WV MADE IN ITALIA Type of yarn Dying process Carded Cashmere Blend Tops Dyed Type of knot Type of packing No knot Cone of about 1,0/1,2 kg - Box of 18 cones Use Use one plie on knitting machine gauge 12 Do not use contrasting colors with stripes knitting Knitting We suggest to use machines with electronic power pack of the yarn. Uniformity The uniformity of yield and of the color are guaranteed for the single dye lot; for each dye lot it is important to inspect each yield and each color. In order to achieve uniformity with sizes, look and handle please kindly proceed always with careful trials for yield on each color taken from production. Knitting stitch density and washing instructions are going to considerably Yield/Pilling influence the final result; we suggest to make trials first in order to value pilling and yield of the garment. Washing In order to obtain the optimum handle and yield of the finished product we we suggest to wash the garments at about 30/35 °C with neutral milling soap for about 3/4 minutes (percentage of milling soap 1 g/L). After proceed with water washing and with a treatment with softener in cold water (as per silicone cationic softener 1 g/L + silicone emulsion 1 g/L.) for about 5/6 minutes. Centrifuge and dry in tumbler at low temperature (max 70/80 °C). We suggest to effect treatment procedure always on the reverse of the garment. We suggest it effect treatment procedure always on the reverse of the garment. We suggest, if necessary, to act on the knitting stitch density and on the time of treatment in order to obtain a homogeneous result according to your needs. If you are going to knit garments with stripes in strong and contrasting colors we suggest to effect first a dry prewash in order to remove the exceeding quantity of color. The following treatment with water must be done considering that the colors are not guaranteed for knitting contrasting shades. Waste It is normal a waste of 3-5%. Claim We do not accept any claim for more than 5 kilos of knitted quantity

for each dve lot